

Ser. No. 10/652,643

## Amendments to the Claims

1. (Currently amended) A method for casting a plurality of blades having an airfoil and a root for securing the blade to a separately-formed disk, the method comprising:
  - forming a plurality of mold sections each having internal surfaces for forming an associated at least one blade of the plurality of blades;
  - assembling the plurality of mold sections; and
  - introducing a molten alloy to the assembled mold sections.
2. (Original) The method of claim 1 wherein:
  - the molten alloy is simultaneously introduced to the assembled mold sections.
3. (Original) The method of claim 1 wherein:
  - each of the mold sections has the internal surfaces for forming only a single such associated blade; and
  - the internal surfaces of each of the mold sections include first surfaces for forming an exterior of the associated blade and second surfaces for forming an interior of the associated blade.
4. (Original) The method of claim 1 wherein the assembling comprises assembling the plurality of mold sections with a distribution manifold.
5. (Original) The method of claim 4 wherein:
  - the molten alloy is introduced so as to settle to an upper level below a lower extreme of flow path portions through the manifold.
6. (Original) The method of claim 4 wherein:
  - the distribution manifold comprises a manifold body having:
    - a pour chamber for receiving molten material; and
    - a plurality of feeder conduits, each extending from the pour chamber toward an

Ser. No. 10/652,643

associated one or more of the mold sections; and  
the assembling comprises positioning each of a plurality of filters in an associated one of the feeder conduits.

7. (Original) The method of claim 1 wherein the forming of each of the mold sections comprises:

assembling a sacrificial blade pattern and a sacrificial gate form atop a plate;  
applying a shell to the assembled blade pattern and gate form; and  
heating the shell to melt at least a portion of each of the blade pattern and gate form.

8. (Currently amended) A method for casting parts comprising:

forming a plurality of mold sections, each section having internal surfaces forming one or more separate ones of said parts;

assembling a cluster of the mold sections that have passed such inspection; and  
assembling a distribution manifold to the cluster, the distribution manifold having:  
a pour chamber for receiving molten material; and  
a plurality of feeder conduits, each extending from the pour chamber toward an associated one or more of the assembled mold sections.

9. (Original) The method of claim 8 further comprising:

inspecting the mold sections and wherein the cluster is assembled from mold sections that have passed such inspection.

10. (Original) The method of claim 9 further comprising:

discarding one or more of the mold sections that have failed such inspection.

11. (Original) The method of claim 8 further comprising:

pouring the molten material into the pour chamber; and  
in a furnace, disassembling the manifold from the cluster and disassembling the cluster.

Ser. No. 10/652,643

12. (Original) The method of claim 8 further comprising:  
pouring the molten material into the pour chamber; and  
permitting the molten material to solidify to consist essentially of a nickel- or cobalt-based superalloy.
13. (Currently amended) A mold assembly comprising:  
a plurality of mold sections; and  
a distribution manifold assembled to the plurality of mold sections and having:  
a pour chamber in a first portion of the manifold for receiving molten material;  
a plurality of feeder conduits, each formed in a branch portion of the manifold,  
unitarily formed as a common piece with the first portion and extending from the pour chamber toward an associated one or more of the plurality of mold sections; and  
a plurality of filters, each positioned in an associated one of the feeder conduits.
14. (Currently amended) The mold assembly of claim 13 wherein:  
there are [[3-4]] exactly three or exactly four such mold sections; and  
there is a single such feeder conduit associated with each of the mold sections.
15. (Original) The mold assembly of claim 13 wherein:  
each mold section comprises a molding cavity and a gate, the gate extending from a lower end at the molding cavity to an upper end coupled to the distribution manifold.
16. (New) The mold assembly of claim 13 wherein:  
the pour chamber is a single, centrally located, chamber.
17. (New) The mold assembly of claim 13 wherein:  
sectional areas of the feeder conduits proximate the filters are dimensioned to provide metering of molten metal from the pour chamber.
18. (New) The mold assembly of claim 13 wherein:

Ser. No. 10/652,643

the plurality of mold sections are separate and assembled to the manifold with distal portions of the branch portions extending into upper ends of feeding passageways in the mold sections.

19. (New) A mold assembly for molding a plurality of parts comprising:
  - a plurality of mold sections, each section having internal surfaces forming one or more separate ones of said parts; and
  - a distribution manifold assembled to the plurality of mold sections and having:
    - a pour chamber for receiving molten material;
    - a plurality of feeder conduits, each extending from the pour chamber toward an associated one or more of the plurality of mold sections; and
    - a plurality of filters, each positioned in an associated one of the feeder conduits.
20. (New) A mold assembly comprising:
  - a plurality of mold sections; and
  - a distribution manifold assembled to the plurality of mold sections and having:
    - a unitarily-formed body defining:
      - a single pour chamber for receiving molten material; and
      - a plurality of feeder conduits, each extending from the pour chamber toward an associated one or more of the plurality of mold sections; and
      - a plurality of filters, each positioned in an associated one of the feeder conduits.